http://www.jourmag.org/index.php/jma

Journal of Magnetism and Its Applications

Received February 16th 2025 received in revised March 11th 2025 accepted April 10th 2025

Research articles

Magnetocaloric Materials for Energy-Efficient Magnetic Refrigeration Systems

Kenji Tanaka
Department of Applied Physics, Kyoto University, Japan

Article info

Keywords:
magnetocaloric effect,
magnetic refrigeration,
magnetic materials,
gadolinium alloys,
LaFeSi compounds,
energy-efficient cooling,
entropy change,
thermal management

Abstract

Energy consumption in cooling technologies has increased significantly with global industrialization and climate change. Conventional vapor-compression refrigeration systems rely on environmentally harmful refrigerants and consume substantial electrical energy. Magnetocaloric refrigeration has emerged as a promising alternative because it utilizes the magnetocaloric effect (MCE), a thermodynamic phenomenon in which certain magnetic materials experience temperature changes when subjected to varying magnetic fields. This article explores the principles, materials, and technological developments associated with magnetocaloric refrigeration systems. Particular attention is given to advanced magnetocaloric materials such as gadolinium alloys, La(Fe,Si) compounds, and Mn-based materials that demonstrate large entropy changes and improved cooling efficiency. The paper also discusses fabrication methods, challenges in device integration, and future directions for energy-efficient cooling technologies. The results indicate that magnetocaloric refrigeration systems have the potential to achieve higher efficiency and environmentally friendly operation compared to traditional cooling technologies.

Introduction

Cooling technologies are essential in modern society, supporting applications ranging from food preservation and medical storage to electronic systems and industrial processes. Traditional refrigeration systems primarily rely on vapor-compression cycles using chemical refrigerants such as hydrofluorocarbons (HFCs). These systems contribute to greenhouse gas emissions and environmental pollution while also consuming significant energy resources. Magnetic refrigeration has emerged as a promising alternative cooling technology based on the magnetocaloric effect (MCE). This phenomenon occurs when certain magnetic materials heat up upon magnetization and cool down when the magnetic field is removed due to changes in magnetic entropy within the material. In magnetic refrigeration systems, magnetocaloric materials act as the working refrigerant. By cyclically applying and removing a magnetic field, heat can be absorbed and released, enabling refrigeration without harmful chemical gases. This approach has the potential to provide environmentally friendly cooling with improved energy efficiency compared to conventional technologies. Recent advances in materials science have significantly improved the performance of magnetocaloric materials, enabling larger temperature changes and higher cooling capacities. Materials such as gadolinium, La(Fe,Si) alloys, and manganese-based compounds have demonstrated promising magnetocaloric properties suitable for room-temperature refrigeration applications. This paper examines the fundamental principles of magnetocaloric refrigeration, explores key magnetocaloric materials, and analyzes the design challenges and technological potential of energy-efficient magnetic refrigeration systems.

Fundamental Principles of the Magnetocaloric Effect

The magnetocaloric effect (MCE) is a thermodynamic phenomenon in which a magnetic material experiences a reversible change in temperature when subjected to a varying magnetic field. This effect originates from the interaction between the magnetic moments of atoms and the external magnetic field. In a magnetic material, the atomic magnetic moments behave like small dipoles that can align or misalign depending on the presence or absence of a magnetic field. When an external magnetic field is applied, these dipoles tend to align with the field direction, reducing the degree of magnetic disorder in the material. This reduction in disorder corresponds to a decrease in magnetic entropy, and according to the laws of thermodynamics, the decrease in entropy results in the release of heat, causing the material's temperature to rise. When the magnetic field is subsequently removed or reduced, the aligned magnetic dipoles return to a more random orientation. This process increases the magnetic entropy of the system and requires the absorption of thermal energy from the surrounding environment. As a result, the temperature of the material decreases. This reversible heating and cooling process is the fundamental mechanism that enables magnetic refrigeration. Unlike conventional refrigeration systems that rely on gas compression and expansion cycles, magnetic refrigeration operates through solid-state thermodynamic processes, which can significantly improve system reliability and reduce environmental impact. The magnitude of the magnetocaloric effect depends on several factors, including the magnetic properties of the material, the strength of the applied magnetic field, and the temperature at which the material undergoes its magnetic phase transition. The most significant magnetocaloric response usually occurs near the Curie temperature, the temperature at which a ferromagnetic material transitions into a paramagnetic state. At this temperature, small changes in the magnetic field can produce large changes in magnetic entropy, resulting in substantial temperature variations. This property is particularly useful for designing efficient cooling systems. In practical magnetic refrigeration systems, the magnetocaloric effect is utilized through a thermodynamic cycle known as the Active Magnetic Regenerator (AMR) cycle. In this process, a magnetocaloric material is repeatedly magnetized and demagnetized while a heat transfer fluid circulates through the system. During magnetization, the material heats up and transfers heat to the surroundings. During demagnetization, the material cools and absorbs heat from the environment that needs to be cooled. Through continuous cycling, this process creates a sustained cooling effect similar to traditional refrigeration systems but with improved energy efficiency and minimal environmental impact. Another important aspect of the magnetocaloric effect is the distinction between adiabatic temperature change and isothermal entropy change. The adiabatic temperature change represents the temperature variation of the material when magnetization occurs without heat exchange with the environment. In contrast, the isothermal entropy change refers to the change in entropy when magnetization occurs at constant temperature. Both parameters are crucial indicators of magnetocaloric performance and are widely used to evaluate the suitability of materials for magnetic refrigeration applications.

*Corresponding author
Email: kenji.tanaka@kyoto-u.ac.jp
DOI: 10.53533/JMA.v2i1.27

Magnetocaloric Materials for Refrigeration

The development of efficient magnetic refrigeration systems largely depends on the discovery and optimization of materials that exhibit strong magnetocaloric properties. Over the past few decades, researchers have investigated a wide range of magnetic materials capable of producing large temperature changes under applied magnetic fields. These materials are typically characterized by significant magnetic entropy changes and strong magnetization transitions near room temperature, making them suitable for practical refrigeration applications. One of the most widely studied magnetocaloric materials is gadolinium (Gd), a rare-earth metal that exhibits a strong magnetocaloric effect near its Curie temperature of approximately 294 K. Gadolinium is often used as a benchmark material in magnetocaloric research because it demonstrates a relatively large entropy change and a noticeable temperature variation when exposed to moderate magnetic fields. Its well-defined magnetic properties and stable crystalline structure have made it a reference material for evaluating new magnetocaloric compounds. However, the high cost and limited availability of rare-earth elements have motivated researchers to explore alternative materials with similar or improved performance. Among the promising alternatives are $La(Fe,Si)_{13}$-based alloys, which have attracted considerable attention due to their giant magnetocaloric effect and tunable Curie temperature. By adjusting the chemical composition and introducing elements such as hydrogen or cobalt, scientists can precisely control the magnetic transition temperature of these alloys. This tunability allows the material to operate efficiently across a range of temperatures, making it suitable for various cooling applications. In addition, La-Fe-Si alloys are relatively less expensive than rare-earth materials, making them attractive for large-scale industrial applications. Another class of promising magnetocaloric materials includes Mn-Fe-P-Si compounds, which demonstrate large entropy changes and strong magneto-structural transitions. These materials undergo simultaneous magnetic and structural phase transformations when exposed to changing magnetic fields, significantly enhancing their magnetocaloric response. Mn-Fe-P-Si alloys are also composed of relatively abundant elements, which reduces production costs and improves their potential for commercial deployment. Furthermore, these materials exhibit good thermal stability and mechanical strength, which are essential for long-term operation in refrigeration systems. In addition to these materials, researchers are also exploring Heusler alloys, rare-earth-free compounds, and nanostructured magnetic materials to further enhance magnetocaloric performance. Nanostructuring techniques can increase surface area and improve heat transfer characteristics, leading to better thermal efficiency in refrigeration systems. Similarly, composite magnetocaloric materials that combine multiple magnetic phases are being developed to broaden the temperature range over which the magnetocaloric effect occurs. The selection of an appropriate magnetocaloric material depends on several factors, including magnetic entropy change, thermal conductivity, mechanical stability, cost, and environmental compatibility. For practical magnetic refrigeration systems, the ideal material should exhibit a large magnetocaloric effect near room temperature, low hysteresis losses, and good heat transfer properties. Continued research in materials science and magnetic engineering is expected to lead to the discovery of new magnetocaloric compounds that can further improve the efficiency and commercial viability of magnetic refrigeration technology.

Magnetic Refrigeration Cycle and System Design

Magnetic refrigeration systems operate based on the magnetocaloric effect and typically utilize a thermodynamic cycle known as the Active Magnetic Regenerator (AMR) cycle. This cycle integrates the magnetocaloric material with a heat transfer medium and a controlled magnetic field to achieve continuous cooling. Unlike traditional refrigeration systems that depend on the compression and expansion of gases, magnetic refrigeration employs solid-state materials whose temperature changes in response to variations in magnetic fields. The AMR cycle is considered one of the most efficient methods for utilizing magnetocaloric materials because it combines heat regeneration and magnetic field control to enhance thermal performance. The cycle begins with the magnetization stage, during which the magnetocaloric material is placed inside a strong magnetic field generated by permanent magnets or electromagnets. When exposed to the magnetic field, the magnetic moments within the material align with the field direction. This alignment reduces the magnetic entropy of the material and results in an increase in temperature. At this stage, the magnetocaloric material becomes hotter than its surrounding environment. To maintain system efficiency, the excess heat generated during magnetization must be removed from the material. The second stage of the cycle is heat rejection. In this phase, a heat transfer fluid, such as water or glycol, flows through the regenerator bed containing the magnetocaloric material. The fluid absorbs the heat released during magnetization and transports it to an external heat sink, such as a cooling radiator or heat exchanger. Effective heat rejection is essential because it ensures that the material returns to a stable baseline temperature before the next phase of the cycle begins. The third stage is demagnetization, which occurs when the external magnetic field is removed or reduced. As the magnetic field decreases, the previously aligned magnetic dipoles within the material return to a disordered state. This process increases the magnetic entropy and causes the material's temperature to drop below its original level. As a result, the magnetocaloric material becomes colder than the surrounding environment, making it capable of absorbing heat from the system that requires cooling. The final stage is heat absorption, where the cooled magnetocaloric material extracts heat from the target environment, such as an air-conditioning system, electronic device, or refrigeration chamber. During this phase, the heat transfer fluid circulates again, transferring heat from the environment to the cooled magnetic material. The cycle then repeats, producing a continuous cooling effect. Through repeated magnetization and demagnetization cycles, the system maintains a stable refrigeration process without relying on conventional refrigerant gases. Efficient system design is crucial for maximizing the performance of magnetic refrigeration systems. Engineers must optimize several components, including the magnet configuration, regenerator geometry, and heat exchanger efficiency. Permanent magnets made from materials such as neodymium–iron–boron (NdFeB) are often used to generate strong magnetic fields while minimizing energy consumption. In addition, advanced regenerator structures are designed to maximize contact between the heat transfer fluid and magnetocaloric materials, improving thermal exchange efficiency. The integration of precise magnetic field control mechanisms and high-performance heat exchangers plays a vital role in achieving stable and efficient cooling cycles.

Fabrication and Engineering Challenges

Although magnetic refrigeration technology has demonstrated promising potential, several technical and engineering challenges must be addressed before large-scale commercialization can occur. One of the primary challenges is the complex synthesis of magnetocaloric materials with optimal magnetic and thermal properties. Many magnetocaloric materials require precise chemical compositions and carefully controlled manufacturing processes to achieve strong entropy changes and stable phase transitions. Small variations in composition or processing conditions can significantly affect the performance of these materials, making large-scale manufacturing difficult. Another significant challenge is the high cost of rare-earth elements, particularly gadolinium, which is widely used in magnetocaloric research due to its strong magnetic properties. Rare-earth metals are expensive and subject to supply chain limitations, which can increase the overall cost of magnetic refrigeration systems. As a result, researchers are actively investigating rare-earth-free magnetocaloric materials composed of more abundant elements such as manganese, iron, and silicon. These alternative materials aim to maintain strong magnetocaloric performance while reducing production costs and improving sustainability. Mechanical properties of magnetocaloric alloys also present challenges. Many promising materials exhibit mechanical brittleness, which makes them susceptible to cracking or structural degradation during repeated magnetization cycles. Since magnetic refrigeration systems operate continuously, the materials must withstand long-term mechanical stress and thermal cycling without losing performance. Researchers are therefore exploring composite structures and reinforced alloys that improve mechanical durability while maintaining magnetocaloric efficiency. Another critical issue involves thermal conductivity and heat transfer efficiency. Magnetocaloric materials often have relatively low thermal conductivity, which can limit the rate at which heat is transferred between the material and the heat transfer fluid. Efficient cooling requires rapid heat exchange, and insufficient thermal conductivity can reduce system performance. To address this challenge, scientists are developing nanostructured materials, porous structures, and composite materials that enhance thermal transport properties. Advances in material engineering and fabrication techniques are expected to play a crucial role in overcoming these challenges. Techniques such as powder metallurgy, additive manufacturing, and nanoengineering are being explored to improve material uniformity and performance. Additionally, researchers are investigating hybrid systems that combine multiple

magnetocaloric materials with different transition temperatures, allowing refrigeration systems to operate efficiently across a wider temperature range.

Environmental and Energy Benefits

Magnetic refrigeration offers several important environmental and energy advantages compared with conventional vapor-compression refrigeration systems. One of the most significant benefits is the elimination of environmentally harmful refrigerants. Traditional refrigeration systems rely on hydrofluorocarbons (HFCs) and other chemical refrigerants that contribute to global warming and ozone depletion. Magnetic refrigeration systems, on the other hand, operate using solid magnetocaloric materials and do not require chemical refrigerants, making them environmentally sustainable. Another major advantage is the potential for higher energy efficiency. Magnetic refrigeration is based on direct thermodynamic processes that reduce energy losses associated with gas compression and expansion cycles. Studies have suggested that magnetic refrigeration systems could achieve significantly higher theoretical efficiency compared with conventional refrigeration technologies, particularly when optimized magnetocaloric materials and advanced system designs are used. Magnetic refrigeration systems also produce lower noise and vibration levels because they do not rely on mechanical compressors. Conventional refrigerators use compressors that generate noise and mechanical vibrations during operation. Magnetic refrigeration systems, in contrast, operate through magnetic field changes and fluid circulation, resulting in quieter and smoother performance. This characteristic makes magnetic refrigeration particularly attractive for applications in residential cooling, medical equipment, and precision electronic systems where low noise levels are desirable. Another benefit is the potential for compact and modular system design. Because magnetocaloric materials can be engineered in various shapes and configurations, magnetic refrigeration systems can be integrated into smaller and more flexible devices. This flexibility allows for innovative cooling solutions in fields such as electronics thermal management, automotive climate control, and portable refrigeration systems. In addition to environmental benefits, magnetic refrigeration technologies contribute to global energy sustainability. Cooling systems account for a significant portion of worldwide electricity consumption, particularly in urban and industrial environments. By improving cooling efficiency and reducing energy demand, magnetic refrigeration can help lower global energy consumption and reduce carbon emissions. As research continues to advance magnetocaloric materials and system designs, magnetic refrigeration is expected to become a viable alternative for next-generation energy-efficient cooling technologies.

Summary

Magnetocaloric refrigeration represents a promising alternative to conventional cooling technologies. By exploiting the magnetocaloric effect in advanced magnetic materials, these systems offer improved energy efficiency and environmentally friendly operation. Materials such as gadolinium alloys, La-Fe-Si compounds, and manganese-based alloys have demonstrated strong magnetocaloric performance suitable for practical refrigeration systems. Although challenges remain in material cost, fabrication complexity, and system integration, ongoing research continues to improve the viability of magnetic refrigeration technologies. As global demand for sustainable cooling solutions increases, magnetocaloric materials are expected to play a significant role in the next generation of energy-efficient refrigeration systems.

References

[1] Pecharsky, V. K., & Gschneidner, K. A. (1999). Magnetocaloric effect and magnetic refrigeration. Journal of Magnetism and Magnetic Materials.
[2] Franco, V., et al. (2018). Magnetocaloric effect: From materials research to refrigeration devices. Progress in Materials Science.
[3] Kitanovski, A. (2020). Energy applications of magnetocaloric materials. Advanced Energy Materials.
[4] Mellari, S., et al. (2023). Introduction to magnetic refrigeration systems. Journal of Thermal Engineering.
[5] Vinod, A., et al. (2024). Evolution of La(Fe,Si) magnetocaloric materials. Materials Science Review.
[6] Tang, X., et al. (2022). Magnetic refrigeration and entropy change in magnetocaloric materials. Nature Communications.
[7] Tishin, A., & Spichkin, Y. (2016). The Magnetocaloric Effect and Its Applications.
[8] Nguyen, T. A., et al. (2025). Thermodynamic efficiency in active magnetic refrigeration systems. Energy Conversion and Management.
[9] Casanova, F. (2017). Fundamentals of magnetocaloric materials. Materials Physics.
[10] Othmani, S., et al. (2012). Magnetocaloric properties of magnetic alloys. EPJ Conferences.
[11] Liu, D. M., et al. (2014). Optimization of MnFePGe magnetocaloric materials. Physical Review Materials.
[12] Duc, N. T. M., et al. (2025). Low-dimensional magnetocaloric materials for energy-efficient refrigeration. Nanomaterials Research.